



ONEGEL



Products may differ in size, colour and appearance to those shown. If you require further information or customisation, please contact us directly.

Dielectric strength	18 kV/mm
Pot life at 23°C min	12
Curing time at 23°C min	20
Volume	300 ml
Туре	ONEGEL
UK-Number	ONEGEL
WISKA-Order no.	10108963
Packing unit	1
ETIM-Classification	EC001168

Remarks:

Colour: Transparent Clear

Mixing Ratio: 1

Describtion:

ONEGEL IP 68 junction box filler, 300ml Cartidge, no mixing required (mono-component silicone gel), ready for immediate use.

Additional Info:

Ready to use, re-enterable, no mixing, excellent electrical insulation, good mechanical strenght, non toxic, no expiry date.

15.01.2024

Your Contact:

WISKA UK Ltd.