

**TITLE:**

Cat6 4pr UTP

CODE:

SFX/C6-UTP-SWA-PE-BLK-1



DESCRIPTION:

1m (per metre) Category 6, 4pr UTP SWA
Black PE

SUPPLIED AS:

Per 1m Lengths

- Capable of 1000mbps transfer speed or 250mhz frequency at a maximum distance of 90 meters
- Unscreened cables are thinner, more flexible and less expensive so are suited to building LANS and telecoms applications
- Polyethylene plastic is excellent for use externally above ground or below ground inside ducting
- Provides mechanical protection against cable being pinched or pierced
- UV resistant



enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23



Product Specification

Cable Construction

CPR	Fca
Conductor	Bare Copper
Conductor Diameter (mm)	0.54 ±0.020
Overall Diameter (mm)	10.50 ±0.20

Insulation

Insulation	HDPE
Insulation Colour	Blue/White/Blue;Orange/White/Orange;Green/White/Green;Brown/White/Brown
Insulation Thickness (mm)	0.29

Outer/Jacket Specification

Outer Jacket	PE UV resistant
Inner Jacket	PE UV resistant
Inner Jacket Colour	Grey RAL 7004
Inner Jacket Diameter (mm)	7.00 ±0.20
Inner Jacket Thickness (mm)	0.7
Overall Colour	Black
Overall Diameter (mm)	10.50 ±0.20
Jacket Colour	Black RAL 9005

Electrical Characteristics

Max Conductor DC resistance @ 20°C	<830/km
Rated Temperature (°C)	-20°C to 80°C






MORE INFORMATION:

EURO CLASS (ca: cable)	CLASSIFICATION CRITERIA		CPR GUIDE	Securi-Flex®	
	FIRE RATING	SFX COMMENT			
Reaction to Fire BS EN ISO 1716			SUBCLASSIFICATIONS FOR EUROCLASSES B _{ca} to D _{ca}		
A_{ca}	Does not contribute to the fire	Due to availability, it will be almost impossible for a cable to meet A _{ca} , so they should only be specified with extreme caution.	(S) SMOKE PRODUCTION	(D) FLAMING DROPLETS	(A) SMOKE ACIDITY
Reaction to Fire BS EN 50399			BS EN 50399/BS EN 61034-2	BS EN 50399	BS EN 60754-2
B1_{ca}	Minimum contribution to the fire	It's highly unlikely the commonly-used cables will be classified to Class B1 _{ca} .	s1a: s1 + transmittance >=80% (BS EN 61034-2) s1b: s1 + transmittance >=60% <80% (BS EN 61034-2) s1: Low production of slow propagation of smoke s2: Intermediate production & propagation of smoke s3: None of the above	d0: No fall of droplets or flaming particles, times for 1200 seconds d1: Fall of droplets or flaming particles that persist for less than 10 seconds, timed for 1200 seconds d2: None of the above	a1: Very low acidity (conductivity <2.5 μS/mm & pH >4.3) a2: low acidity (conductivity <10 μS/mm & pH >4.3) d2: None of the above
B2_{ca}	Combustible, low flame spread & heat release contribution to the fire	Similar to Class C _{ca} , although a lower acceptable heat release rate and burn measurement. In practice, this is likely to be the highest class cables will meet.			
C_{ca}	Combustible, moderate flame spread & heat release	This is a more rigorous test than Class D _{ca} , this is widely accepted across Europe as the 'go to' classification, but be aware, many cables do not meet Class C _{ca} though availability is improving.			
D_{ca}	Combustible, moderate flame spread & heat release	This classification has relatively little use or acceptance within specifying/contracting organisations. This is because no large scale fire growth is measured.			
Reaction to Fire BS EN 60332-1-2			Visit us online: www.securiflex.co.uk The Trusted Cable Brand		
E_{ca}	Combustible, limited fire spread of less than 425mm	A basic test for vertical flame propagation for a single insulated wire or cable using a 1 KW pre-mixed flame. Note: This test does not measure heat release, toxic fumes or smoke.	Classes A to E have to be tested by an independent authorised laboratory. Most cables will fall into classes B2 _{ca} to E _{ca} . For a cable to meet A _{ca} , B1 _{ca} , B2 _{ca} or C _{ca} , there also needs to be regular on-going factory audits.		
F_{ca}	Combustible, fire spread of more than 425mm	Cables classified to Class F _{ca} may have high levels of flammability due to the materials they are made of. This does not mean that the cable cannot be used, it is more likely to be used external.			

OUR OPERATING TEMPERATURE RANGE GUIDE



Securi-Flex®



enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23