

STRIDENT⁺ BATTERIES

GP12-3.2FR 12V 3.2Ah(20hr)

The rechargeable batteries are lead-acid, with flame-resistant casing and flame-arrestor vents, designed to prevent fire propagation and meet strict safety codes in sensitive installations. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore maintenance-free and leak proof. Batteries should be installed and operated in the upright position only.



Battery Construction


Component	Positive Plate	Negative Plate	Container	Cover	Safety Value	Terminal	Separator	Electrolyte
Raw Material	Lead Dioxide	Lead	ABS	ABS	Rubber	T1	Fibreglass	Sulfuric Acid

General Features

- Positive and negative plates in lead-calcium-tin alloy.
- Stable Quality & High Reliability
- Sealed Construction.
- Long Service Life.
- Maintenance-Free Operation
- Low Pressure Venting System
- Low Self Discharge
- U.L. and CE Component Recognition
- Design life 10 Years
- Flame Retardant (UL V0) ABS Container

Dimensions and Weight

Length (mm/inch)	134/5.28
Width (mm/inch)	67/2.64
Height (mm/inch)	59/2.32
Total Height (mm/inch)	65/2.64
Approx. Weight (kg/lbs)	1.22/2.56



Terminal T1

Performance Characteristics

- Nominal Voltage: 12V
- Number of Cells: 6
- Nominal Capacity 77°F (25°C)
 - 20 Hour Rate (10.5V): 3.2Ah
 - 10 Hour Rate (10.5V): 3.0Ah
 - 1 Hour Rate (9.60V): 2.08Ah
- Internal Resistance
 - Fully Charged Battery 77°F (25°C) 55m Ohms
- Capacity affected by temperature (20hr)
 - 40°C - 102%
 - 25°C - 100%
 - 0°C - 85%
 - 15°C - 65%
- Self-Discharge
 - 3 Month: Remaining Capacity: 91%
 - 6 Month: Remaining Capacity: 82%
 - 12 Month: Remaining Capacity: 65%
- Operating Temperature Range
 - Discharge: -15~ 50°C
 - Charge: -10~ 50°C
 - Storage: -20~ 50°C
- Max. Discharge Current 77°F (25°C): 48A (5s)
- Charge methods: Cyclic charging voltage 77°F (25°C)
 - Cycle use: 14.50 to 14.90V
 - Maximum charging current: 0.96A
 - Temperature Compensation: -30mV/°C
- Float charging voltage: 13.60 to 13.80V
 - Temperature compensation: -18mV/°C

Strident

50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD
Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com



STRIDENT[™]
INNOVATIONS

www.strident.uk.com

STRIDENT⁺ BATTERIES

GP12-3.2FR 12V 3.2Ah(20hr)

Discharge Data

Discharge Constant Current (Amperes at 77°F/25°C)									
End Point Volts/Cell	10min	15min	30min	1h	2h	3h	5h	10h	20h
9.60V	7.68	6.08	3.39	2.08	1.14	0.82	0.55	0.30	0.16
9.90V	7.45	5.93	3.32	2.05	1.13	0.81	0.55	0.30	0.16
10.2V	7.14	5.72	3.22	2.00	1.12	0.81	0.55	0.30	0.16
10.5V	6.84	5.52	3.14	1.96	1.10	0.80	0.54	0.30	0.16
10.8V	6.45	5.23	3.03	1.90	1.08	0.78	0.53	0.29	0.16

The above characteristics data are average values obtained with three charge/discharge cycles, not the minimum values.

Discharge Constant Power (Qatts at 77°F/25°C)									
End Point Volts/Cell	10min	15min	30min	1hr	2hr	3h	5h	10h	20h
9.60V	86.6	69.3	38.9	24.1	13.3	9.69	6.63	3.62	1.95
9.90V	84.0	67.6	38.1	23.7	13.2	9.64	6.59	3.61	1.94
10.2V	80.6	65.2	36.9	23.1	13.1	9.57	6.54	3.59	1.93
10.5V	77.1	62.9	36.0	22.7	12.9	9.50	6.50	3.57	1.92
10.8V	72.8	59.6	34.7	22.0	12.6	9.22	6.30	3.50	1.88

The above characteristics data are average values obtained with three charge/discharge cycles, not the minimum values.

Strident

50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD
Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com



STRIDENT[™]
INNOVATIONS


www.strident.uk.com

STRIDENT⁺


BATTERIES

GP12-3.2FR 12V 3.2Ah(20hr)


Discharge Characteristics(25°C)




Charging Characteristics(25°C)




Effect of Temperature on Capacity




Self-discharge Characteristics




The Relationship for Open Circuit Voltage and Residual Capacity (25°C)




The Relationship for Charging Voltage and Temperature



Floating Life on Temperature



Cycle Life on D.O.D(25°C)



Strident

50 Turbine Way, Eco Tech Business & Innovation Park, Swaffham, Norfolk, PE37 7XD
Tel: +44 (0)1362 300102 | Fax: +44 (0)1362 300103 | Email: sales@strident.uk.com



STRIDENT
INNOVATIONS

www.strident.uk.com